

Application No.: 10/660207  
Docket No.: DC8503USNA

JAN 18 2007

Page 2

Amendments to Claims

## Claims 1-9 (Canceled)

10. (Currently amended): The conductive flow field separator plate of claim 9 23, wherein the liquid crystal polymer is liquid crystalline polyester.
11. (Original): The conductive flow field separator plate of claim 10, wherein the conductive filler is graphite filler or carbon nanotubes.
12. (Original): The conductive flow field separator plate of claim 11, wherein the graphite filler is selected from the group consisting of graphite fibre filler, graphite powder filler and mixtures thereof.
13. (Canceled)
14. (Currently amended): The conductive flow field separator plate of claim 9 23, wherein the poly(styrene-co-maleic anhydride) contains from about 1% to about 75%; ~~preferably from about 1% to 50%, most preferably from about 1% to about 32%;~~ maleic anhydride moieties.
15. (Withdrawn): A method of making a conductive flow field separator plate having reduced resistivity, comprising the steps of:
  - (a) blending a liquid crystal polymer, poly(styrene-co-maleic anhydride) and conductive filler together to form a blend; and
  - (b) moulding the blend to form the conductive flow field separator plate.
16. (Withdrawn): The method of claim 15, wherein step (a) comprising blending the following components:
  - (a) from about 0.5 wt% to about 40 wt%, preferably from about 1 wt% to about 30 wt%, most preferably from about 5 wt% to about 20 wt%, of the liquid crystal polymer;
  - (b) from about 0.5 wt% to about 40 wt%, preferably from about 1 wt% to about 30 wt%, most preferably from about 5 wt% to about 20 wt% of the poly(styrene-co-maleic anhydride); and
  - (c) from about 20 wt% to about 99 wt%, preferably from about 60 wt% to about 98 wt%, most preferably from about 70 wt% to about 90 wt% of the conductive filler.

Application No.: 10/660207

Docket No.: DC8503USNA

Page 3

17. (Withdrawn): The method of claim 16, wherein the conductive flow field separator plate is formed by compression moulding, extrusion moulding or injection moulding.
18. (Withdrawn): The method of claim 16, wherein the liquid crystal polymer is liquid crystalline polyester.
19. (Withdrawn): The method of claim 16, wherein the conductive filler is graphite filler or carbon nanotubes.
20. (Withdrawn): The method of claim 19, wherein the graphite filler is selected from the group consisting of graphite fibre filler, graphite powder filler and mixtures thereof.
21. (Withdrawn): The method of claim 16, wherein the poly(styrene-co-maleic anhydride) is poly(styrene-co-maleic anhydride).
22. (Withdrawn): The method of claim 16, wherein the poly(styrene-co-maleic anhydride) contains from about 1% to about 75%, preferably from about 1% to 50%, most preferably from about 1% to about 32%, maleic anhydride moieties.
23. (New): A conductive flow field separator plate, comprising:
  - (a) from about 0.5 wt% to about 40 wt% of liquid crystal polymer;
  - (b) from about 0.5 wt% to about 40 wt% of poly(styrene-co-maleic anhydride);  
and
  - (c) from about 20 wt% to about 99 wt% of conductive filler.
24. (New): The conductive flow field separator plate of claim 23, wherein said plate comprises:
  - (a) from about 1 wt% to about 30 wt% of the liquid crystal polymer;
  - (b) from about 1 wt% to about 30 wt% of the poly(styrene-co-maleic anhydride);  
and
  - (c) from about 60 wt% to about 98 wt% of the conductive filler.

Application No.: 10/660207

Docket No.: DC8503USNA

Page 4

25. (New): The conductive flow field separator plate of claim 24, wherein said plate comprises:
- (a) from about 5 wt% to about 20 wt% of the liquid crystal polymer;
  - (b) from about 5 wt% to about 20 wt% of the poly(styrene-co-maleic anhydride); and
  - (c) from about 70 wt% to about 90 wt% of the conductive filler.
26. (New): The conductive flow field separator plate of claim 14, wherein the poly(styrene-co-maleic anhydride) contains from about 1% to about 50% maleic anhydride moieties.
27. (New): The conductive flow field separator plate of claim 14, wherein the poly(styrene-co-maleic anhydride) contains from about 1% to about 32% maleic anhydride moieties.